Pache SARL - 64 Route de Gravin, 74300 Magland
04 50 89 57 17 contact@pache-adler.fr
www.pache-adler.fr

Technical data sheet

ADLER
Paint runs through our veins.

Alkydharzturbo 8054

Solvent-based hardener for **synthetic resin coating systems** and **oils** , for **trade use**

PRODUCT DESCRIPTION

Product numbers

8054000210

General

Solvent-based hardener for transparent and opaque synthetic resin coating systems and oils; improves mechanical and chemical resistance and enhances drying under unfavourable climatic drying conditions (temperature, humidity) and on woods that are rich in active substances.

Application area

Hardener component for solvent-based synthetic resin paints/varnishes (e.g. Vivido Expresslack (4504), Vivido Samtalkyd (4514), Vivido Brilliantalkyd (4503), Ferro GSX (4505))

Hardener component for solvent-based ADLER Pullex products (e.g. Pullex Color (4403), Pullex Renovier-Grund (4416), Pullex Plus-Lasur (4415), Pullex Top-Lasur (4421), etc.)

PROCESSING

Processing instructions

- Immediately after adding Alkydharzturbo (8054) to the paint component, blend in carefully.
- Mixed paints and stains must be processed as specified in the corresponding technical data sheet.
- Do not close containers with hardened material.

Pot life

8 hour(s)

Mixed coatings can be processed within one working day.

Increased temperatures reduce the pot life.

Blending ratio

8054000210

100 parts by weight of ADLER Pullex products
5-10 parts by weight Alkydharzturbo (8054)

100 parts by weight of all other approved products
5-10 parts by weight Alkydharzturbo (8054)

ORDERING INFORMATION

Size of trading unit

250 ml, 500 ml, 1 l

PACHE Sarl

ADLER-Werk Lackfabrik, A-6130 Schwaz
Fon: +43/5242/6922-190, Fax: +43/5242/6922-309, Mail: technical-support@adler-lacke.com

Our instructions are based on the current state of knowledge and are intended to advise the buyer/user to the best of our knowledge, but must be individually adapted to the areas of application and processing conditions. The buyer/user is responsible for deciding on the suitability and use of the supplied product, which is why we recommend that a sample be produced to check the suitability of the product. In all other respects, our General Terms and Conditions of Sale apply. All previous data sheets lose their validity with this edition. We reserve the right to make changes to container sizes, color shades and available gloss levels.

Pache SARL - 64 Route de Gravin, 74300 Magland
04 50 89 57 17 contact@pache-adler.fr
www.pache-adler.fr

FURTHER DETAILS

Durability / storage



Min. 1 year(s) in the original sealed containers.

Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 °C).

Immediately seal the container to prevent humidity from penetrating.

Close opened containers well and use up the content as soon as possible.

Safety information

The product is only suitable for the industrial and professional use.

Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at **www.adler-lacke.com.**

PACHE sarl