Pache SARL - 64 Route de Gravin, 74300 Magland
04 50 89 57 17 contact@pache-adler.fr
www.pache-adler.fr

Technical data sheet

ADLER
Paint runs through our veins.

Aquafix Blue-Patina 8139

Ready-to-use **oxidation solution** for **non-ferrous metals** for **professional and industrial use**

PRODUCT DESCRIPTION

Product numbers

8139000210

General

Water-based, ready-to-use oxidation solution for non-ferrous metal surfaces to achieve oxidation effects.

Special properties and standards

- **French ordinance DEVL1104875A**
  Marking of construction coating products for their emission of volatile pollutants: A+

Application area



To achieve oxidation effects on non-ferrous metals or on coatings containing non-ferrous metals.

Application in combination with a suitable topcoat system.

PROCESSING

Processing instructions

- The temperature of the product and object, and the room temperature must be at least + 15 °C.
- Aquafix Blue-Patina (8139) is applied directly onto the prepared real-metal surface.
- Do not use metal containers!
- Only use rustproof work tools!
- Any change in the processing sequence, environmental conditions, non-observance of instructions or the use of products not listed may have an unfavourable effect on the result.

Application technique

Application method	Spray bottle
Application quantity	uneven

Application is carried out irregularly, either locally or over the surface, using a spray bottle on the real-metal surface.

The application quantity depends on the desired effect.

After complete drying of Aquafix Blue-Patina (8139), the process can be repeated.

PACHE sarl

ADLER-Werk Lackfabrik, A-6130 Schwaz
Fon: +43/5242/6922-190, Fax: +43/5242/6922-309, Mail: technical-support@adler-lacke.com

Our instructions are based on the current state of knowledge and are intended to advise the buyer/user to the best of our knowledge, but must be individually adapted to the areas of application and processing conditions. The buyer/user is responsible for deciding on the suitability and use of the supplied product, which is why we recommend that a sample be produced to check the suitability of the product. In all other respects, our General Terms and Conditions of Sale apply. All previous data sheets lose their validity with this edition. We reserve the right to make changes to container sizes, color shades and available gloss levels.

Drying times
(at 23 °C and 50 % rel. humidity)

Recoatable after	approx. 12 hour(s)

The figures given above are reference values. Drying depends on the substrate, layer thickness, temperature, air exchange, relative humidity, stacking pressure and stacking conditions.

Cleaning the working equipment

With water immediately after use.

SUBSTRATE

Type of substrate

Chipboard panels and MDF boards or base boards coated with primer film.

Substrate property

The substrate must be dry, clean, capable of holding the paint, free from separating substances such as grease, wax, silicone, resin etc. and free from wood dust, as well as tested for suitability for coating.

Substrate preparation

Grit size 240

COATING SYSTEM

Primer coat

1 x Bluefin Isospeed (3134) (two-component) or Aduro Ecofill (2416)

Intermediate sanding

Grit size 280 – 320

Intermediate sanding must be carried out immediately before the subsequent coating is applied in order to ensure good intermediate adhesion!

Remove sanding dust.

Intermediate coat



500 g/m² ADLER Real Metal mixture

Making the Real Metal mixture:

Step 1:

100 parts by weight of	Bluefin Pure-Metal (3133000210)
5 parts by weight of	Aqua-Hardener 8450 (8450000210)

Carefully stir Aqua-Hardener 8450 (8450000210) into Bluefin Pure-Metal (3133000210) (approx. 3 mins).

Step 2:

Carefully work 250 parts by weight of Aquafix Ferro, Kupfer, Messing, Bronze or Zinn into the paint/hardener mixture, stirring all the time and making sure there are no lumps.

Stirring is best done by machine using a basket agitator.

Pot life

The mixture can be used for approx. 2 - 3 hours if kept at room temperature.

PACHE sarl

Intermediate drying time	Intermediate drying: approx. 5 hour(s) at approx. 20 °C (preferably) overnight
Finishing treatment (sanding, polishing, buffing)	Multi-stage sanding with finish sandpaper grit size 180 / 240 / 360 / 600 The method of application and in particular the sanding process play a major part in determining the resulting effect. Sanding may not be done on a sanding machine or using a hand sanding machine with dust extraction: fire risk and risk of discolouration of subsequent coats of paint through rust formation! Remove sanding dust.
Product application	Aquafix Blue-Patina (8139) Application is carried out irregularly, either locally or over the surface, using a spray bottle on the real-metal surface. The quantity required will depend on the desired effect. After complete drying of Aquafix Blue-Patina (8139), the process can be repeated.
Intermediate drying time	Intermediate drying time: approx. 12 hours (over night) The topcoat should be applied within 24 hours, without intermediate sanding.
Topcoat	3 x Aduro Antiscratch G10 (2517000110) Intermediate drying: approx. 2 hour(s)

ORDERING INFORMATION

Size of trading unit	500 ml
Supplementary products	Aduro Antiscratch (2517) Aduro Ecofill (2416) Aqua-Hardener 8450 (8450) Aquafix Bronze (8137) Aquafix Kupfer (8135) Aquafix Messing (8136) Aquafix Zinn (8138) Bluefin Isospeed (3134) Bluefin Pure-Metal (3133) Please refer to the corresponding technical data sheets of the products.

FURTHER DETAILS

Durability / storage 	Min. 1 year(s) in the original sealed containers. Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 °C). Close opened containers well and use up the content as soon as possible.
Safety information	The product is only suitable for the industrial and professional use. The inhalation of paint aerosols during spray application must generally be avoided. This is ensured by the proper use of a respirator (combination filter A2/P2). Avoid contact with skin and eyes. During work, wear fastened-up working clothes, protective gloves made of butyl rubber and safety goggles with side protection!

PACHE Sarl

If the product comes into contact with your eyes, rinse immediately with water and consult a doctor!

Remove dirty, soaked clothing immediately!

If the product comes into contact with your skin, wash off immediately with plenty of soap and water!

Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at **www.adler-lacke.com.**

PACHE sarl