Pache SARL - 64 Route de Gravin, 74300 Magland
04 50 89 57 17 contact@pache-adler.fr
www.pache-adler.fr

Technical data sheet

ADLER
Paint runs through our veins.

ADLER Clean-Multi-Refresher 8317

Effective **cleaner, refresher and degreyer** for weathered and greyed wood, plastic, stone and masonry based on oxalic acid for **DIY and professional use**

PRODUCT DESCRIPTION

General

The slightly thixotropic product acts as an effective cleaner, degreyer and brightener and restores the wood to its original colour (by means of bleaching agent). Biodegradable. Contamination, wood extractives and discolouration caused by metals can be gently removed.
Intact coatings are not attacked.

Special properties and standards

- **French ordinance DEVL1104875A** regarding the marking of construction coating products for their emission of volatile pollutants: A+

Application areas



- For the treatment of weathered and greyed wood, e. g. garden furniture, terraces, timber cladding, balconies, etc.
- Preliminary treatment of tropical wood, which is rich on wood extractives.
- For the treatment of dirty masonry.
- For the treatment of dirty plastics.

PROCESSING

Instructions for use



- Please shake the product before use.
- The temperature of the product and object, and the room temperature must be at least + 5 °C.
- The optimal conditions for use are between 15 – 25 °C with a relative atmospheric humidity between 40 – 80 %.
- Apply the product saturated.
- Do not process it under conditions of intense sunlight, rain, extremely high humidity, strong wind or pending frost. Cover those surfaces well that are not to be treated.

PACHE sarl

ADLER-Werk Lackfabrik, A-6130 Schwaz
Phone: 0043/5242/6922-301, Fax: 0043/5242/6922-309, email: technical-support@adler-lacke.com

Our instructions for use are based on knowledge available currently and shall guide the buyer/user to the best of one's knowledge, but, however, must be clarified for the areas of application and processing conditions on a case-to-case basis. The buyer/user is responsible for deciding on the suitability and use of the delivered product, which is why it is recommended to produce a sample to check the suitability of the product. Our general terms and conditions of sale are otherwise applicable. All previous data sheets are rendered invalid with the issue of this one. Rights reserved for the modification of the container sizes, colour shades and degrees of gloss available.

Application technique

Application method	Brushing (paint brush)	Spraying	Brushing
Yield per application (m²/l)[1)]	For degreying: approx. 5 For cleaning: approx. 5 - 20		
Dilution (thinning)	water		
Thinner amount added in %	For degreying: no dilution For cleaning: until 15% (maximum 1:5) depending on the impurity		
[1)] yield without addition of thinner			

The shape, the properties and moisture of the substrate affect the consumption/yield. Accurate values for consumption must be obtained by applying trial coats in advance.

Cleaning the working equipment

With water immediately after use.

SUBSTRATE

Preparation of the substrate

Remove weathered coatings; cover adjacent plants and sensitive surfaces which should not be cleaned or rinse immediately with water after use.

Pre-water absorbent substrates.

COATING SYSTEM

Product application

1 x ADLER Clean-Multi-Refresher 8317

Wood:
Impact time 10 - 20 minutes while keeping the surface always humid (for example with aerosol).

Wash afterwards with lots of water and with mechanical support (nylon- or coarse scrubbing brush; do not use metallic brushes). The mechanical support is necessary to remove also deep pore contamination.

In the case of strongly discoloured surfaces, we recommend using the product twice.

Intermediate drying time: approx. 3 days.

Masonry and synthetic materials
Impact time 10 - 20 minutes and then rinse with plenty of water and mechanical support.

Intermediate drying time: approx. 24 hours

Synthetic materials
Impact time 10 - 20 minutes and then rinse with plenty of water and mechanical support.

Intermediate drying time: approx. 2 hours

Intermediate sanding

If necessary, the wood fibres can be smoothed with sandpaper or abrasive fleece before repainting.

PACHE sarl

Subsequent coating	Corresponding ADLER wood coating or desired Aviva facade paint. Please observe the relative technical data sheets of the products.
	ORDERING INFORMATION
Size of trading unit	1.0 l; 2.5 l; 500 ml (spray bottle)
Colour shades / degrees of gloss	Leicht blau eingefärbt (slightly blue coloured) 8317000210
	FURHTER DETAILS
Durability / storage 	At least 3 years in the original sealed containers. Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 °C). Do not transfer the contents into metal containers.
Safety-related information information	Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at **www.adler-lacke.com.** It is recommended to use safety gloves and safety glasses while processing.

PACHE sarl