Pache SARL - 64 Route de Gravin, 74300 Magland
04 50 89 57 17 contact@pache-adler.fr
www.pache-adler.fr

Technical data sheet

ADLER
Paint runs through our veins.

ADLER PUR-Struktureffekt-Pasten 90155 ff

Structure paste for solvent-based **coating systems** for **industrial and professional** use

PRODUCT DESCRIPTION

General

Structural effect pastes for pigmented solvent-based PUR coatings such as ADLER Pigmopur 24005 ff to achieve structural effect surfaces. The product is formulated without the addition of aromatic solvents.

Application areas



- For durable surfaces with structural effect throughout the entire interior.

PROCESSING

Instructions for use

- Please stir the product before use.
- ADLER PUR-Struktureffekt-Pasten 90155 ff must be carefully stirred into the unhardened and undiluted paint; then incorporate hardener and the required dilution quantity.
- Mixed paints must be processed as specified in the corresponding technical data sheet.
- ADLER PUR-Struktureffekt-Pasten 90155 ff leads - depending on the quantity used - to a noticeable reduction in the gloss of the original paint.
- The overcoating of varnish layers containing ADLER PUR-Struktureffekt-Pasten 90155 ff is possible (without intermediate sanding, within 24 hours, approx. 80 - 100 g/m²); however, the structure is reduced. Suitable overspray varnish: for example ADLER Pigmotop 25361 ff

Quantity to be added

5 to max. 10 percent by weight to paint.

PACHE sarl

10-18 (supersedes 07-18) ZKL 9034

ADLER-Werk Lackfabrik, A-6130 Schwaz
Fon: 0043/5242/6922-301, Fax: 0043/5242/6922-309, Mail: technical-support@adler-lacke.com

Our instructions for use are based on knowledge available currently and shall guide the buyer/user to the best of one's knowledge, but, however, must be clarified for the areas of application and processing conditions on a case-to-case basis. The buyer/user is responsible for deciding on the suitability and use of the delivered product, which is why it is recommended to produce a sample to check the suitability of the product. Otherwise our General Terms of Sale apply. All previous data sheets are rendered invalid with the issue of this one. Rights reserved for the modification of the container sizes, colour shades and degrees of gloss available.

Pache SARL - 64 Route de Gravin, 74300 Magland
04 50 89 57 17 contact@pache-adler.fr
www.pache-adler.fr

Drying times
(at 23 °C and 50 % rel. humidity)

The drying of the coating systems is not influenced by adding PUR-Struktureffekt-Pasten 90155.

Recoatable	after approx. 1 hour

Cleaning the working equipment

With ADLER DD-Verdünnung 80019 or ADLER Waschverdünnung 80077.

ORDERING INFORMATION

Size of trading unit

400 g

Refinements

ADLER PUR-Struktureffekt-Paste fein 90155
ADLER PUR-Struktureffekt-Paste grob 90156

FURTHER DETAILS

Durability / storage



At least 1 year in the original sealed containers.

Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 °C).

Safety-related information

Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at **www.adler-lacke.com.**

The product is only suitable for industrial and professional use.

PACHE Sarl